
# **FOAMBOARD**












#### **Application**

There are two different methods used for the internal insulation of exterior walls: Plaster method and dry plaster method. For plaster method, the boards are adhered by cement based fixing mortar to the inner wall surface in a manner that the joints are aligned. The application is completed by adhering waste strip to the joint. For dry plaster method, the boards faced with 1,25 cm gypsum board on one side, are adhered to the wall by cement based fixing mortar. Before the adhering application, roughness of the wall surface should be minimized.

After the boards are adhered, the application is completed by standard connection and finish techniques. For the internal insulation of the exterior walls, it is important to take precautions to avoid thermal bridges at where the slabs, columns, beams and curtains connect to the exterior wall.

Thickness (cm)	Width x Length (cm)	Package (m²)			
2,5	60 x 125	12,00			
3	60 x 125	10,50			
4	60 x 125	7,50			
5	60 x 125	6,00			
6	60 x 125	5,25			
7	60 x 125	4,50			
8	60 x 125	3,75			
9	60 x 125	3,75			
10	60 x 125	3,00			
12	60 x 125	2,25			
15	60 x 125	1,50			



Exterior wall ①
Fixing mortar ②

Plastic anchor ③

Foamboard 4

Plaster or gypsum board 5



- · High thermal insulation
- Easy to apply
- Available in different sizes
- Water impermeable



## **TECHNICAL DATA SHEET**

### Izocam Foamboard 1500 P - 2000 P - 2500 P - 3000 P - 3500 P

Properties	Symbol	Unit	Description					Tolerance	Standard
Material	-	-		Extr	uded Polysty	/rene		-	TS EN 13164
Edge Profile	-	-	Square, Ship-lap					-	-
Surface Shape	-	-	Rough					-	-
Material Type	-	-	1500 P	2000 P	2500 P	3000 P	3500 P	-	-
Compressive Strength (10 % deformation)	σ <sub>10</sub>	kPa	min. 150	min. 200	min. 250	min. 300	min. 350	CS(10/Y) 150 200 - 250 - 300	TS EN 826
Density	ρ	kg/m³	min. 20-21	min. 24-30	min. 26-30	min. 27-30	min. 28-32	-	-
Tensile Strength Perpendicular to Faces	TR	kPa	min. 200	min. 200	min. 400	min. 400	min. 600	TR200 - TR400 TR 600	TS EN 1607
Water Vapor Diffusion Resistance Coefficient	MU	-	80	80	100	100	100	MU80 - MU100	TS EN 12086
Width	w	mm	600					± 8 mm	TS EN 822
Length	ı	mm	1250					± 8 mm	TS EN 822
Squareness	S <sub>b</sub>	mm/m	max. 5					-	TS EN 824
Flatness	S <sub>max</sub>	mm/m	max. 6					-	TS EN 825
1500 P 2000 P 2500 P 3000 P 3500 P	t	mm	25 30   	40 50 40 50 40 50 40 50 40 50	60 70 60 70 60 70 60 70	80 90 80 90 80 90 80 90	- - - 120	T1 *	TS EN 823
Reaction to fire	-	-	<u>'</u>	, ,	-	TS EN 13501-1			
Thermal Resistance	R <sub>D</sub>	m².K/W	0,70 0,85	1,10 1,40	1,70 2,00	2,25 2,55	3,40		TS EN 13164
Declared Thermal Conductivity (10 °C)	$\lambda_{_{\mathrm{D}}}$	W/m.K	0,035					-	TS EN 13164
Freeze Thaw Resistance	FTCD	%	max. 2					FTCD <sub>2</sub>	TS EN 12091
Dimensional Stability Under Specified Thermal and Humidity Conditions	$\begin{array}{c} \Delta\epsilon_{_{I}},\Delta\epsilon_{_{b}},\\ \Delta\epsilon_{_{d}} \end{array}$	%	max. 5 **					DS (70,90)	TS EN 1604
Dimensional Stability Under Specified Thermal and Compressive Load conditions	ε,	%	max. 5 ***					DLT(1)5 DLT(2)5	TS EN 1605
Long Term Water Absorption with Total Immersion	W <sub>it</sub>	%	max. 0,7					WL(T)0,7	TS EN 12087
Long Term Water Absorption with Diffusion	W <sub>dV</sub>	%	max. 5					WD(V)5	TS EN 12088
Packaging Material	-	-	PE Film					-	-
Other Information	Densities change according to thickness for detailed information contact with Izocam.								

- $^\star$  T1 : +2 for < 50 mm; -2,+3 for 50 120 mm; -2,+3 for > 120 mm. According to customer demands can be produced in T2 or T3 thickness class.
- \*\* TS EN 13164 / Item 4.3.2
- \*\*\* TS EN 13164 / Item 4.3.3

#### Safety Reminders for Loading, Unloading, Shipping and Storing

- Loading and unloading should be done by (at least) two people.
- The packages should be put on top of each other with extra care.
- Only backshutter of the truck body should be opened during unloading.
- Unloading should be carried out from backside to the front.
- Products should not be put into upright position during shipping and storing.
- Products should not be pulled by their package.
- Products should not be stepped on.
- The packages should be put on the floor with extra care so the corners of the product especially is not damaged by a hit.
- Storing can be carried out by superposing the products with or without pallets.
- Products should not be shipped with the materials containing organic solvents (thinner, paint, fuel oil, acetone, etc.).
- Combustible, flammable, hazardous materials should not be stored in storage area and there should be fire extinguishing equipment available.

Izocam is not responsible for any problem because of misprinting. Izocam, the manufacturer, reserves the right to alter product specifications without prior notice. Izocam also manufactures special products upon request. For your requirements, you are requested to contact our Export Department.

