

İZOCAMFLEX PIPE



It is an elastomeric rubber based insulation material in the form of pipe with closed cell structure. It is manufactured to be used for air conditioning, heating and cooling systems.

Application

It is used at the exterior surfaces of the ducts in the heating, cooling, ventilating and air conditioning systems for thermal insulation and condensation control purposes. The pipe to be insulated and the rubber surface should fit properly and no gap should be left in between. Joints should be tightly sealed. The application should be protected against disruption and rupture. For the applications exposed to sun, a protective coat or a protective paint should be used against UV affect. For the outdoor applications, the surface should be coated within 5 days.

Inner Diameter	Copper Pipe	Steel Pipe	Thickness (mm)				
			6	9	13	19	25
mm	inch	inch					
6	1/4"		+	+	+		
8	5/16"		+	+	+		
10	3/8"	1/8"	+	+	+	+	
12	1/2"		+	+	+	+	
15	5/8"	1/4"	+	+	+	+	
18	3/4"	3/8"	+	+	+	+	+
20			+				
22	7/8"	1/2"	+	+	+	+	+
25	1"		+	+	+	+	+
28	1 1/8"	3/4"	+	+	+	+	+
35	1 3/8"	1"	+	+	+	+	+
42	1 5/8"	1 1/4"		+	+	+	+
48		1 1/2"		+	+	+	+
54	2 1/8"			+	+	+	+
60	2 3/8"	2"		+	+	+	+
64	2 1/2"			+	+	+	+
70	2 5/8"			+	+	+	+
76	3"	2 1/2"		+	+	+	+
80	3 1/8"			+	+	+	+
89	3 1/2"	3"		+	+	+	+
102		3 1/2"		+	+	+	+
108	4 1/4"			+	+	+	+
114	4 1/2"	4"		+	+	+	+



- High thermal insulation
- High condensation control
- CFC free
- Environment friendly
- Highly flexible



TECHNICAL DATA SHEET

İzocamflex Pipe

Properties	Symbol	Unit	Description	Tolerance**	Standard					
Material	-	-	Elastomeric Rubber Foam Tube	-	TS EN 14304					
Length	l	mm	2000 ≤ L ≤ 50000 *	± 1,5 %	TS EN 822					
Inner Diameter	D _{i,D}	mm	≤ 100	D _{i,D} + 1 ≤ D _i ≤ D _{i,D} + 4	TS EN 13467					
			> 100	D _{i,D} + 1 ≤ D _i ≤ D _{i,D} + 6						
Thickness	t	mm	6 ≤ d ≤ 25	d _D ≤ 8	±1,0	TS EN 823				
				8 < d _D ≤ 18	±1,5					
				18 < d _D ≤ 25	±2,5					
Facing	-	-	Unfaced	-	-					
Reaction to fire	-	-	B _L -s3,d0	-	TS EN 13501-1					
Declared Thermal Conductivity	T	°C	-10	0	25	40	60	80	-	TS EN 12667
	λ _D	W/m.K	0,033	0,034	0,036	0,039	0,041	0,042		
Max. Service Temperature	-	°C	-50 / 105						-	-
Water Vapor Diffusion Resistance Factor	μ	-	≥ 7000						-	TS EN 12086
Packaging Material	-	-	Carton Box						-	-

* Standard product length is 2m.

** Tolerances comply with TS EN 14304 standard.

İzocam Elastomeric Rubber Foam Products are manufactured in İZOCAM Eskişehir Plant having ISO 9001, ISO 14001 and ISO 45001 Management System Certificates.

Please contact İzocam Sales Department for different sizes, special facings and detailed technical properties.

Product and its specifications discussed herein are subject to change by İZOCAM without notice.

Safety Reminders for Loading, Unloading, Shipping and Storing

- These operations should be done indoors in case of rainy weather conditions.
- Loading and unloading should be done by (at least) two people.
- The products should be wrapped by a waterproof cover during shipping.
- Boxes should be carried by their handles.
- When the boxes piled in the truck body are being tied up hard padding (wood, cardboard, etc.) should be put on the corners of the packages to protect them against possible damages by ropes.
- The corners should be aligned when the boxes are superposed.
- Only backshutter of the truck body should be opened during unloading.
- Storing should be done indoors and the boxes should be put over flat floor.
- Maximum 5 boxes should be superposed.
- Boxes should not be put into upright position.
- Boxes should not be stepped on and should not be used as steps.
- Products should not be unloaded by pushing or throwing from the truck.
- The truck should not be moved without wrapping and binding the packages.
- The products should not be exposed to sun.
- Storage area should not be wet.

İzocam is not responsible for any problem because of misprinting. İzocam, the manufacturer, reserves the right to alter product specifications without prior notice. İzocam also manufactures special products upon request. For your requirements, you are requested to contact our Export Department.

